

Shin-Etsu Silicone

Silicone Products for Personal Care

1 Dimethyl Silicone Fluids	2	11 Polyether Modified Silicones	5
2 Volatile Silicones		12 Polyglycerin Modified Silicones	
3 Methyl Phenyl Silicone Fluids		13 Silicone Gels	6
4 Amino Modified Silicones	3	14 Silicone Acrylates	7
5 Other Modified Silicone		15 Trimethylsiloxysilicates	
6 Fluid Compounds		16 Silicone Powders	8
7 Dimethyl Silicone Blends		17 Powder Treatment Agents	
8 High Polymerization Dimethiconol	4	18 Inorganic Powder Dispersions	9
9 Amino Gums			
10 Silicone Emulsions			

1 Dimethyl Silicone Fluids

Grade	Parameter	INCI	Viscosity 25°C mm ² /s	Specific Gravity 25°C	Refractive Index 25°C	Volatile Matter 150°C/24h %	Pour Point °C	Flash Point °C
KF-96A-1cs		TRISILOXANE	1	0.818	1.382	Boiling point 153°C	-86	37
KF-96L-1.5cs		DIMETHICONE	1.5	0.853	1.388	Boiling point 190°C	-86	64
KF-96L-2cs		DIMETHICONE	2	0.852	1.388	—	< -60	88
KF-96A-5cs		DIMETHICONE	5	0.915	1.396	—	< -60	102
KF-96A-6cs		DIMETHICONE	6	0.925	1.397	—	< -60	174
KF-96A-10cs		DIMETHICONE	10	0.935	1.399	30	< -60	176
KF-96A-20cs		DIMETHICONE	20	0.950	1.400	< 5.0	< -60	264
KF-96A-30cs		DIMETHICONE	30	0.955	1.401	< 1.5	< -55	280
KF-96A-50cs		DIMETHICONE	50	0.960	1.402	< 0.5	< -50	> 300
KF-96A-100cs		DIMETHICONE	100	0.965	1.403	< 0.5	< -50	> 300
KF-96A-200cs		DIMETHICONE	200	0.970	1.403	< 0.5	< -50	> 315
KF-96A-300cs		DIMETHICONE	300	0.970	1.403	< 0.5	< -50	> 315
KF-96A-350cs		DIMETHICONE	350	0.970	1.403	< 0.5	< -50	> 315
KF-96A-500cs		DIMETHICONE	500	0.970	1.403	< 0.5	< -50	> 315
KF-96-1,000cs		DIMETHICONE	1,000	0.970	1.403	< 0.5	< -50	> 315
KF-96-3,000cs		DIMETHICONE	3,000	0.970	1.403	< 0.5	< -50	> 315
KF-96A-5,000cs		DIMETHICONE	5,000	0.975	1.403	< 0.5	< -50	> 315
KF-96H-6,000cs		DIMETHICONE	6,000	0.975	1.403	< 0.5	< -50	> 315
KF-96H-10,000cs		DIMETHICONE	10,000	0.975	1.403	< 0.5	< -50	> 315
KF-96H-12,500cs		DIMETHICONE	12,500	0.975	1.403	< 0.5	< -50	> 315
KF-96H-30,000cs		DIMETHICONE	30,000	0.976	1.403	< 0.5	< -50	> 315
KF-96H-50,000cs		DIMETHICONE	50,000	0.976	1.403	< 0.5	< -50	> 315
KF-96H-60,000cs		DIMETHICONE	60,000	0.976	1.403	< 0.5	< -50	> 315
KF-96H-100,000cs		DIMETHICONE	100,000	0.977	1.403	< 0.5	< -50	> 315
KF-96H-300,000cs		DIMETHICONE	300,000	0.977	1.403	< 0.5	< -50	> 315
KF-96H-500,000cs		DIMETHICONE	500,000	0.978	1.403	< 0.5	< -50	> 315
KF-96H-1,000,000cs		DIMETHICONE	1,000,000	0.978	1.403	< 0.5	< -50	> 315

* The commercial name in US is DM-FLUID-xxx, outside of US is KF-96-xxx.

(Not specific values)

2 Volatile Silicones

Grade	Parameter	INCI	Viscosity 25°C mm ² /s	Specific Gravity 25°C	Refractive Index 25°C	Freezing Point °C	Boiling Point °C	Flash Point °C	Surface Tension 25°C mN/m
KF-995		CYCLOPENTASILOXANE	4.0	0.96	1.396	-40	210	77	17.8

(Not specific values)

3 Methyl Phenyl Silicone Fluids

Grade	Parameter	INCI	Viscosity 25°C mm ² /s	Specific Gravity 25°C	Refractive Index 25°C	Volatile Matter 150°C/24h %	Pour Point °C	Flash Point °C
KF-53		DIPHENYL DIMETHICONE	175	1.055	1.485	< 0.3	< -30	> 300
KF-54		DIPHENYL DIMETHICONE	400	1.070	1.505	< 0.3	< -30	> 300
KF-56A		DIPHENYLSILOXY PHENYL TRIMETHICONE	15	0.995	1.498	15*	< -55	> 100

* 105°C/3h

(Not specific values)

4 Amino Modified Silicones

Parameter Grade	INCI	Viscosity 25°C mm ² /s	Specific Gravity 25°C	Refractive Index 25°C
KF-8004	AMODIMETHICONE	800	0.980	1.408
KF-8015	AMINOPROPYL DIMETHICONE	50,000-100,000	0.975	1.405
KF-867S	AMODIMETHICONE	1,300	0.980	1.407

(Not specific values)

5 Other Modified Silicone

Parameter Grade	INCI	Modified Type	Melting Point °C	Specific Gravity 25°C
KF-7002	STEAROXYMETHICONE/DIMETHICONE COPOLYMER	Stearoxy	40-50	0.890

(Not specific values)

6 Fluid Compounds

Parameter Grade	INCI	Appearance	Viscosity 25°C mPa·s	Specific Gravity 25°C
KS-66	SIMETHICONE	Light gray translucent liquid	300	1.01
KS-69	SIMETHICONE	Light gray translucent paste	2,500	1.01

(Not specific values)

7 Dimethyl Silicone Blends

Parameter Grade	INCI	Component A Component B	Viscosity 25°C mPa·s	Specific Gravity 25°C	Refractive Index 25°C	Dimethicone Gum Content %	Solvent
KF-9008	DIMETHICONE		30,000	0.961	1.397	20	KF-995
	CYCLOPENTASILOXANE						
KF-9011	DIMETHICONE		1,600	0.959	1.397	10	KF-995
	CYCLOPENTASILOXANE						
KF-9013	DIMETHICONE		15,000	0.954	1.401	15	KF-96A-20cs
	DIMETHICONE						
KF-9014	DIMETHICONE		6,000	0.960	1.397	15	KF-995
	CYCLOPENTASILOXANE						
MK-15H	DIMETHICONE		45,000	0.958	1.402	20	KF-96A-20cs
	DIMETHICONE						
X-21-5495	DIMETHICONE		3,000	0.961	1.397	15	KF-995
	CYCLOPENTASILOXANE						
KF-9028	DIMETHICONE		3,000	0.965	1.398	20	KF-995
	CYCLOPENTASILOXANE						
KF-9030	DIMETHICONE		5,000	0.955	1.401	20	KF-96A-20cs
	DIMETHICONE						

(Not specific values)

8 High Polymerization Dimethiconol

Grade	Parameter	INCI	Component A	Viscosity 25°C mPa·s	Specific Gravity 25°C	Refractive Index 25°C	Dimethiconol Content %	Solvent
			Component B					
X-21-5613		DIMETHICONOL DIMETHICONE		5,000	0.957	1.401	20	KF-96A-20cs
X-21-5666		DIMETHICONOL CYCLOPENTASILOXANE		15,000	0.960	1.398	30	KF-995
X-21-5849		DIMETHICONOL		100,000	0.977	1.403	100	—

(Not specific values)

9 Amino Gums

Grade	Parameter	INCI	Component A	Viscosity 25°C mm ² /s	Specific Gravity 25°C	Refractive Index 25°C	Amino Gum Content %	Solvent
			Component B					
KF-8017		AMINOPROPYL DIMETHICONE DIMETHICONE		2,000	0.956	1.401	10	KF-96A-20cs
KF-8018		AMINOPROPYL DIMETHICONE CYCLOPENTASILOXANE		2,000	0.961	1.397	10	KF-995
KF-8020		AMINOPROPYL DIMETHICONE DIMETHICONE		40,000	0.956	1.401	20	KF-96A-20cs

(Not specific values)

10 Silicone Emulsions

Grade	Parameter	INCI	Composition %	Appearance	Viscosity 25°C mPa·s	Base Oil	Silicone Solvent	Silicone Content %	PH 25°C	Ionic Property
KM-901		Component A : DIMETHICONE Others	50.0	Milky white emulsion	100	KF-96H- 60,000cs	—	50	3.0	Nonionic
			6.25							
KM-902		Component A : DIMETHICONE Others	50.0	Milky white emulsion	100	KF-96H- 500,000cs	—	50	3.0	Nonionic
			6.15							
KM-903		Component A : DIMETHICONE Component B : DIMETHICONE Others	18.0	Milky white emulsion	1,000	Dimethicone gum	KF-96A- 200cs	60	3.0	Nonionic
			42.0							
			6.25							
KM-906A		Component A : DIMETHICONE Others	45.0	Milky white emulsion	1,000	KF-96H- 100,000cs	—	50	5.0	Anionic
			10.6							
KM-910		Component A : DIMETHICONE Component B : DIMETHICONE Others	36.0	Milky white emulsion	2,500	Dimethicone gum	KF-96A- 200cs	60	5.0	Nonionic
			24.0							
			6.75							
KM-9729		Component A : DIMETHICONE/VINYL DIMETHICONE CROSSPOLYMER Others	50.0	Milky white emulsion	—	Silicone rubber powder	—	50	5.0	Nonionic
			2.75							
X-52-2042		Component A : DIMETHICONE Component B : DIMETHICONE Others	33.0	Milky white emulsion	1,000	Dimethicone gum	KF-96A- 200cs	60	3.0	Nonionic
			27.0							
			6.25							

(Not specific values)

Silicone Emulsions

Parameter Grade	INCI	Composition %	Appearance	Viscosity 25°C mPa·s	Base Oil	Silicone Solvent	Silicone Content %	PH 25°C	Ionic Property
X-52-2127	Component A : DIMETHICONE	30.0	Milky white emulsion	4,000	Dimethicone gum	KF-96A-200cs	75	7.0	Cationic
	Component B : DIMETHICONE	45.0							
	Others	4.5							
X-52-2162	Component A : DIMETHICONE	26.0	Milky white emulsion	3,000	Dimethicone gum	KF-96A-200cs	65	3.5	Nonionic
	Component B : DIMETHICONE	39.0							
	Others	5.25							
X-52-2265	Component A : AMODIMETHICONE	40.0	Milky white emulsion	—	Amino modified silicone	—	40	6.0	Nonionic
	Others	10.1							
X-52-2328	Component A : AMINOPROPYL DIMETHICONE	12.0	Milky white emulsion	2,000	Amino modified gum	KF-96A-20cs	60	7.0	Nonionic
	Component B : DIMETHICONE	48.0							
	Others	9.5							

(Not specific values)

11 Polyether Modified Silicones

Parameter Grade	INCI	Viscosity 25°C mm ² /s	Specific Gravity 25°C	Refractive Index 25°C	Calculated HLB wt % EO/5	Cloud Point °C
KF-6011	PEG-11 METHYL ETHER DIMETHICONE	130	1.07	1.450	14.5	65
KF-6011P	PEG-11 METHYL ETHER DIMETHICONE	140	1.07	1.450	14.5	65
KF-6012	PEG/PPG-20/22 BUTYL ETHER DIMETHICONE	1,600	1.03	1.446	7.0	35
KF-6013	PEG-9 DIMETHICONE	400	1.03	1.436	10.0	—
KF-6015	PEG-3 DIMETHICONE	150	1.00	1.420	4.5	—
KF-6016	PEG-9 METHYL ETHER DIMETHICONE	150	1.01	1.417	4.5	—
KF-6017	PEG-10 DIMETHICONE	600	1.01	1.420	4.5	—
KF-6017P	PEG-10 DIMETHICONE	850	1.01	1.420	4.5	—
KF-6004	PEG-32 METHYL ETHER DIMETHICONE	Solid (melting point 45°C)	—	—	9.0	—
KF-6028	PEG-9 POLYDIMETHYLSILOXYETHYL DIMETHICONE	900	1.00	1.420	4.0	—
KF-6028P	PEG-9 POLYDIMETHYLSILOXYETHYL DIMETHICONE	900	1.00	1.420	4.0	—
KF-6038	LAURYL PEG-9 POLYDIMETHYLSILOXYETHYL DIMETHICONE	700	0.96	1.430	3.0	—
KF-6043	PEG-10 DIMETHICONE	400	1.09	1.454	14.5	71

* P Grade: odorless versions created using an improved deodorization process.

(Not specific values)

12 Polyglycerin Modified Silicones

Parameter Grade	INCI	Viscosity 25°C mPa·s	Specific Gravity 25°C	Refractive Index 25°C	Estimated HLB
KF-6100	POLYGLYCERYL-3 DISILOXANE DIMETHICONE	40,000	1.08	1.458	Medium
KF-6104	POLYGLYCERYL-3 POLYDIMETHYLSILOXYETHYL DIMETHICONE	4,000	1.00	1.409	Low
KF-6105	LAURYL POLYGLYCERYL-3 POLYDIMETHYLSILOXYETHYL DIMETHICONE	4,000	0.95	1.426	Low

(Not specific values)

13 Silicone Gels

Parameter Grade	INCI	Component A	Appearance	Penetration (worked) 25°C	Refractive Index 25°C	Base Oil	Crosspolymer %
		Component B					
KSG-15	DIMETHICONE/VINYL DIMETHICONE CROSSPOLYMER		Colorless transparent paste	420	1.397	KF-995	4-10
	CYCLOPENTASILOXANE						
USG-103	DIMETHICONE/VINYL DIMETHICONE CROSSPOLYMER		Colorless transparent paste	350	1.398	KF-995	8-12
	CYCLOPENTASILOXANE						
KSG-16	DIMETHICONE/VINYL DIMETHICONE CROSSPOLYMER		Colorless translucent paste	330	1.400	KF-96A-6cs	20-30
	DIMETHICONE						
KSG-1610	DIMETHICONE/VINYL DIMETHICONE CROSSPOLYMER		Colorless translucent paste	380	1.389	TMF-1.5	15-20
	METHYL TRIMETHICONE						
USG-106	DIMETHICONE/VINYL DIMETHICONE CROSSPOLYMER		Colorless transparent paste	420	1.418	ISODODECANE	8-12
	ISODODECANE						
KSG-18A	DIMETHICONE/PHENYL VINYL DIMETHICONE CROSSPOLYMER		Colorless transparent paste	330	1.495	KF-56A	10-20
	DIPHENYLSILOXY PHENYL TRIMETHICONE						
KSG-41	VINYL DIMETHICONE/LAURYL DIMETHICONE CROSSPOLYMER		Colorless translucent paste	400	1.455	MINERAL OIL	25-35
	MINERAL OIL						
KSG-42	VINYL DIMETHICONE/LAURYL DIMETHICONE CROSSPOLYMER		Colorless translucent paste	380	1.422	ISODODECANE	20-30
	ISODODECANE						
KSG-43	VINYL DIMETHICONE/LAURYL DIMETHICONE CROSSPOLYMER		Colorless translucent paste	400	1.442	TRIETHYLHEXANOIN	25-35
	TRIETHYLHEXANOIN						
KSG-44	VINYL DIMETHICONE/LAURYL DIMETHICONE CROSSPOLYMER		Colorless translucent paste	380	1.447	SQUALANE	25-35
	SQUALANE						
KSG-210	DIMETHICONE/PEG-10/15 CROSSPOLYMER		Colorless milky white paste	400	1.403	KF-96A-6cs	20-30
	DIMETHICONE						
KSG-240	DIMETHICONE/PEG-10/15 CROSSPOLYMER		Colorless milky white paste	400	1.400	KF-995	15-25
	CYCLOPENTASILOXANE						
KSG-310	PEG-15/LAURYL DIMETHICONE CROSSPOLYMER		Colorless milky white paste	400	1.450	MINERAL OIL	25-35
	MINERAL OIL						
KSG-320	PEG-15/LAURYL DIMETHICONE CROSSPOLYMER		Colorless milky white paste	400	1.420	ISODODECANE	20-30
	ISODODECANE						
KSG-330	PEG-15/LAURYL DIMETHICONE CROSSPOLYMER		Colorless milky white paste	395	1.442	TRIETHYLHEXANOIN	15-25
	TRIETHYLHEXANOIN						
KSG-340	PEG-10/LAURYL DIMETHICONE CROSSPOLYMER PEG-15/ LAURYL DIMETHICONE CROSSPOLYMER		Colorless milky white paste	430	1.445	SQUALANE	25-35
	SQUALANE						
KSG-710	DIMETHICONE/POLYGLYCERIN-3 CROSSPOLYMER		Colorless milky white paste	400	1.400	KF-96A-6cs	20-30
	DIMETHICONE						
KSG-810	LAURYL DIMETHICONE/POLYGLYCERIN-3 CROSSPOLYMER		Colorless milky white paste	380	1.450	MINERAL OIL	25-35
	MINERAL OIL						
KSG-820	LAURYL DIMETHICONE/POLYGLYCERIN-3 CROSSPOLYMER		Colorless milky white paste	340	1.420	ISODODECANE	20-30
	ISODODECANE						
KSG-830	LAURYL DIMETHICONE/POLYGLYCERIN-3 CROSSPOLYMER		Colorless milky white paste	380	1.442	TRIETHYLHEXANOIN	15-25
	TRIETHYLHEXANOIN						
KSG-840	LAURYL DIMETHICONE/POLYGLYCERIN-3 CROSSPOLYMER		Colorless milky white paste	380	1.445	SQUALANE	25-35
	SQUALANE						

(Not specific values)

14 Silicone Acrylates

Parameter Grade	INCI	Component A	Viscosity 25°C mm ² /s	Content %	Solvent
		Component B			
KP-541	ACRYLATES/DIMETHICONE COPOLYMER		500-10,000 mPa·s	60	ISOPROPYL ALCOHOL
	ISOPROPYL ALCOHOL				
KP-543	ACRYLATES/DIMETHICONE COPOLYMER		100-1,000	50	BUTYL ACETATE
	BUTYL ACETATE				
KP-545	ACRYLATES/DIMETHICONE COPOLYMER		100-500	30	KF-995
	CYCLOPENTASILOXANE				
KP-549	ACRYLATES/DIMETHICONE COPOLYMER		500-5,000	40	TMF-1.5
	METHYL TRIMETHICONE				
KP-550	ACRYLATES/DIMETHICONE COPOLYMER		100-3,000	40	ISODODECANE
	ISODODECANE				
KP-578	ACRYLATES/ETHYLHEXYL ACRYLATE/ DIMETHICONE METHACRYLATE COPOLYMER		150-200	100	—
KP-561P	ACRYLATES/STEARYL ACRYLATE/ DIMETHICONE METHACRYLATE COPOLYMER		Solid (melting point 25-35°C)	100	—
KP-562P	ACRYLATES/BEHENYL ACRYLATE/ DIMETHICONE METHACRYLATE COPOLYMER		Solid (melting point 45-55°C)	100	—

(Not specific values)

15 Trimethylsiloxysilicates

Parameter Grade	INCI	Component A	Viscosity 25°C mm ² /s	Specific Gravity 25°C	Refractive Index 25°C	Resin Content %	Solvent	Film Hardness
		Component B						
KF-7312J	TRIMETHYLSILOXYSILICATE		120	1.050	1.405	50	KF-995	Hard
	CYCLOPENTASILOXANE							
KF-7312K	TRIMETHYLSILOXYSILICATE		5,000	1.070	1.410	60	KF-96A-6cs	Hard
	DIMETHICONE							
KF-7312T	TRIMETHYLSILOXYSILICATE		50	1.009	1.400	60	TMF-1.5	Hard
	METHYL TRIMETHICONE							
X-21-5249	TRIMETHYLSILOXYSILICATE		60	1.034	1.404	50	KF-995	Medium
	CYCLOPENTASILOXANE							
X-21-5250	TRIMETHYLSILOXYSILICATE		60	1.034	1.404	50	KF-995	Soft
	CYCLOPENTASILOXANE							
KF-9021	TRIMETHYLSILOXYSILICATE		2,000	1.070	1.406	50	KF-995	Very hard
	CYCLOPENTASILOXANE							
X-21-5595	TRIMETHYLSILOXYSILICATE		35	0.967	1.416	60	ISODODECANE	Hard
	ISODODECANE							
X-21-5616	TRIMETHYLSILOXYSILICATE		10	0.916	1.412	60	ISODODECANE	Soft
	ISODODECANE							

(Not specific values)

16 Silicone Powders

Parameter Grade	INCI	Appearance	Volatile Content 105°C/3h %	True Specific Gravity	Average Particle Size μm	Hardness Durometer A
KMP-590	POLYMETHYLSILSESQUIOXANE	White spherical powder	1.0	1.32	2	—
KMP-591	POLYMETHYLSILSESQUIOXANE	White spherical powder	1.0	1.32	5	—
KMP-598	DIMETHICONE/ VINYL DIMETHICONE CROSSPOLYMER	White spherical powder	0.1	0.97	13	30
KMP-400	DIMETHICONE/ VINYL DIMETHICONE CROSSPOLYMER	White amorphous powder	0.1	0.97	30	30
KSP-100	VINYL DIMETHICONE/ METHICONE SILSESQUIOXANE CROSSPOLYMER	White spherical powder	0.1	1.00	5	30
KSP-101	VINYL DIMETHICONE/ METHICONE SILSESQUIOXANE CROSSPOLYMER	White spherical powder	0.1	0.98	12	30
KSP-102	VINYL DIMETHICONE/ METHICONE SILSESQUIOXANE CROSSPOLYMER	White spherical powder	0.1	0.98	30	30
KSP-105	VINYL DIMETHICONE/ METHICONE SILSESQUIOXANE CROSSPOLYMER	White spherical powder	0.1	0.99	2	75
KSP-300	DIPHENYL DIMETHICONE/VINYL DIPHENYL DIMETHICONE/SILSESQUIOXANE CROSSPOLYMER	White spherical powder	0.1	1.11	5	40

(Not specific values)

17 Powder Treatment Agents

Parameter Grade	INCI	Viscosity 25°C mm ² /s	Specific Gravity 25°C	Refractive Index 25°C	Volatile Matter 105°C/3h %
KF-99P	METHICONE	20	1.00	1.396	< 5
KF-9901	HYDROGEN DIMETHICONE	20	0.97	1.398	< 5
KF-9908	TRIETHOXYSIYLETHYL POLYDIMETHYLSILOXYETHYL DIMETHICONE	60	0.97	1.412	< 5
KF-9909	TRIETHOXYSIYLETHYL POLYDIMETHYLSILOXYETHYL HEXYL DIMETHICONE	45	0.96	1.415	< 5
KP-574	ACRYLATES/TRIDECYL ACRYLATE/TRIETHOXYSIYLPROPYL METHACRYLATE/DIMETHICONE METHACRYLATE COPOLYMER	300	0.98	1.416	< 5
AES-3083	TRIETHOXYCAPRYLYLSILANE	2	0.88	1.417	Boiling point 100°C/2mmHg

(Not specific values)

18 Inorganic Powder Dispersions

Parameter Grade	INCI	Powder	Solvent	Powder Content wt %	Appearance	Viscosity 25°C mPa·s	Specific Gravity 25°C
SPD-T5	CYCLOPENTASILOXANE	TiO ₂	KF-995	40	White-light gray fluid	< 4,000	1.3
	TITANIUM DIOXIDE						
	POLYGLYCERYL-3 POLYDIMETHYLSILOXYETHYL DIMETHICONE						
	ALUMINUM HYDROXIDE						
	STEARIC ACID						
SPD-Z5	ZINC OXIDE	ZnO	KF-995	60	White-light yellow fluid	< 4,000	1.7
	CYCLOPENTASILOXANE						
	POLYGLYCERYL-3 POLYDIMETHYLSILOXYETHYL DIMETHICONE						
	TRIETHOXYSILYLETHYL POLYDIMETHYLSILOXYETHYL HEXYL DIMETHICONE						

(Not specific values)


Dimethyl silicone fluid soluble in various solvents

KF-96 (dimethyl silicone fluid) : Solubility of medium viscosity grades
 Note that low viscosity grades of KF-96 (5mm²/s and below) also dissolve in ethanol and other solvents, so check prior to use.


Solvent	Result
Solvent naphtha	Soluble
Industrial Gasoline	Soluble
Mineral Spirits	Soluble
Kerosene	Soluble
Cyclohexane	Soluble
n-Hexane	Soluble
n-Heptane	Soluble
Ethyl Ether	Soluble
Diisopropyl Ether	Soluble
Hexyl Ether	Soluble
Ethyl Acetate	Soluble
Butyl Acetate	Soluble
Isopropyl Ether	Soluble
Isopropyl Laurate	Soluble
Isopropyl Palmitate	Soluble
Isopropyl Myristate	Soluble
Methyl Ethyl Ketone	Soluble
Methyl Isobutyl Ketone	Soluble
Lauryl Alcohol	Soluble
Acetone	Partially Soluble
Dioxane	Partially Soluble
Butanol	Partially Soluble
2-Ethylhexanol	Partially Soluble
Amyl Acetate	Partially Soluble
Glacial Acetate Acid	Partially Soluble
Naphthene-based Lubricating Oils	Partially Soluble
Methanol	Insoluble
Ethanol	Insoluble
Cyclohexanol	Insoluble
Ethylene Glycol	Insoluble
Carbitol	Insoluble
Glycerin	Insoluble
Diethylene Glycol Stearate	Insoluble
Propylene Glycol	Insoluble
Liquid Paraffin	Insoluble
Paraffin Wax	Insoluble
Petrolatums	Insoluble
Lubricating Oils	Insoluble
Fatty Acid (other than Glacial Acetic Acid)	Insoluble
Animal and Vegetable Oils	Insoluble
Methyl Phthalate	Insoluble
Water	Insoluble

Volatile Data

■ Volatility at 25°C (measured by filter paper method)




■ Volatility at 37°C (measured by filter paper method)



Bake-on Temperature and Processing Time Methyl Hydrogen Polysiloxane

(without solvent)



* Testing Condition
 Processing Liquid: 10 % KF-99P Solution
 Testing Substrate: Glass

Solubility Dimethicone

KF-96L-KF-96

Composition Rate Silicone Fluid Cosmetic Ingredient	Silicone Fluid : Cosmetic Ingredient					
	10:1		1:1		1:10	
	KF-96L*	KF-96	KF-96L*	KF-96	KF-96L*	KF-96
Cetyl Alcohol	S	I	S	I	S	I
Bees Wax	I	I	I	I	S	I
Lanolin	I	I	I	I	I	I
Glycerine	I	I	I	I	I	I
Liquid Paraffin	S	I	S	I	S	I
Stearic Acid	P	I	I	I	I	I
Squalane	S	S	S	I	S	I
Jojoba Oil	S	I	P	I	P	I
Vaseline	I	I	I	I	S	I

S: Soluble P: Soluble at 60 to 80°C I: Insoluble

* KF-96L: KF-96A (1 – 5)

Compatibility (20%) Polyether Modified Silicone Fluid, Polyglycerin Modified Silicone Fluid

	KF-6011 KF-6011P	KF-6012	KF-6013	KF-6015	KF-6016	KF-6017 KF-6017P	KF-6028 KF-6028P	KF-6038	KF-6043	KF-6100	KF-6104	KF-6105
KF-96A-6cs (Dimethicone)	I	I	PS	I	S	S	S	S	I	PS	S	S
TMF-1.5 (Methyl Trimethicone)	I	I	I	S	S	S	S	S	I	PS	S	S
KF-995 (Cyclopentasiloxane)	I	I	I	S	S	S	S	S	I	PS	S	S
KF-56A (Diphenylsiloxy Phenyl Trimethicone)	S	S	PS	S	S	S	S	S	I	I	S	S
Mineral Oil	I	PS	I	I	PS	PS	PS	S	I	I	I	S
Isotridecyl Isononanoate	I	S	S	S	S	S	S	S	I	PS	S	S
Triethylhexanoin	S	S	S	S	S	S	S	S	S	PS	PS	S
Ethyl Alcohol	S	S	S	S	S	S	S	PS	S	S	PS	PS
Isopropyl Alcohol	S	S	S	S	S	S	S	S	S	S	S	S
Propylene Glycol	S	I	S	I	I	S	I	PS	S	S	I	I
1, 3-Butylene Glycol	S	I	S	I	I	S	I	PS	S	S	PS	PS
Glycerin	I	I	I	I	I	I	I	PS	I	S	PS	PS
Water	S	S	I	I	I	I	I	I	S	G	I	I

S: Soluble PS: Partially Soluble I: Insoluble G: Gel

Handling Precaution

Quality, Storage and Handling

- Since changes in quality may occur due to exposure to heat, humidity, light or acidic or alkaline environments, be sure to close tightly and store in a cool, dark location.
- Do not leave products in an open state while working.
- Please read the Material Safety Data Sheet (MSDS) before use. MSDS can be obtained from our Sales Department.

Silicone Division Sales and Marketing Department I

6-1, Ohtemachi 2-chome, Chiyoda-ku, Tokyo, Japan

Phone : +81-(0)3-3246-5132 Fax : +81-(0)3-3246-5361

Shin-Etsu Silicones Europe B. V.

Bolderweg 32, 1332 AV, Almere, The Netherlands

Phone : +31-(0)36-5493170 Fax : +31-(0)36-5326459

Shin-Etsu Silicone Taiwan Co., Ltd.

Hung Kuo Bldg. 11F-D, No. 167, Tun Hua N. Rd.,

Taipei, 10549 Taiwan, R.O.C.

Phone : +886-(0)2-2715-0055 Fax : +886-(0)2-2715-0066

Shin-Etsu Silicone Korea Co., Ltd.

Danam Bldg., 9F, 120, Namdaemunno5(o)-ga,

Jung-gu, Seoul 100-704, Korea

Phone : +82-(0)2-775-9691 Fax : +82-(0)2-775-9690

Shin-Etsu Singapore Pte. Ltd.

4 Shenton Way, #10-03/06, SGX Centre II, Singapore 068807

Phone : +65-6743-7277 Fax : +65-6743-7477

Shin-Etsu Silicones (Thailand) Ltd.

7th Floor, Harindhorn Tower, 54 North Sathorn Road,

Bangkok 10500, Thailand

Phone : +66-(0)2-632-2941 Fax : +66-(0)2-632-2945

Shin-Etsu Silicone International Trading (Shanghai) Co., Ltd.

29F Junyao International Plaza, No.789,

Zhao Jia Bang Road, Shanghai

Phone : +86-(0)21-6443-5550 Fax : +86-(0)21-6443-5868

- The data and information presented in this catalog may not be relied upon to represent standard values. Shin-Etsu reserves the right to change such data and information, in whole or in part, in this catalog, including product performance standards and specifications without notice.
- Users are solely responsible for making preliminary tests to determine the suitability of products for their intended use. Statements concerning possible or suggested uses made herein may not be relied upon, or be construed, as a guaranty of no patent infringement.
- The silicone products described herein have been designed, manufactured and developed solely for general industrial use only; such silicone products are not designed for, intended for use as, or suitable for, medical, surgical or other particular purposes. Users have the sole responsibility and obligation to determine the suitability of the silicone products described herein for any application, to make preliminary tests, and to confirm the safety of such products for their use.
- Users must never use the silicone products described herein for the purpose of implantation into the human body and/or injection into humans.
- Users are solely responsible for exporting or importing the silicone products described herein, and complying with all applicable laws, regulations, and rules relating to the use of such products. Shin-Etsu recommends checking each pertinent country's laws, regulations, and rules in advance, when exporting or importing, and before using the products.
- Please contact Shin-Etsu before reproducing any part of this catalog.
Copyright belongs to Shin-Etsu Chemical Co., Ltd.



The Development and Manufacture of Shin-Etsu Silicones are based on the following registered international quality and environmental management standards.

Gunma Complex ISO 9001 ISO 14001
(JCQA-0004 JCQA-E-0002)

Naoetsu Plant ISO 9001 ISO 14001
(JCQA-0018 JCQA-E-0064)

Takefu Plant ISO 9001 ISO 14001
(JQA-0479 JQA-EM0298)

<http://www.silicone.jp/>